

FLAT FLOAT GLASS

BACKGROUND OF THE INVENTION

1. Field of the Invention:

This invention relates to a flat float glass that can be prestressed or transformed into a glass ceramic with high quartz mixed crystals or keatite mixed crystals.

2. Background of the Invention:

Numerous applications of glass require flat glass, e.g. glass in the form of glass sheets or panels to be used as view windows and for display purposes. These flat glass items are manufactured from molten glass using methods of the prior art such as rolling, drawing, casting and floating.

On account of high surface quality requirements, special importance has been acquired by float glass, which is widely used in the glass industry. In the manufacture of glass sheets using the float glass method, a ribbon of glass is drawn from the glass-melting furnace and then, to smooth the surface, the glass, while still deformable, is drawn over a metal bath (e.g. consisting of molten tin). The glass thereby "floats" on the liquid metal. After it is removed from the metal bath, the glass sheet is cooled and then cut to length into individual segments. The result is a flat glass that has parallel and fire-polished surfaces and a high surface quality.

Using the float glass method, flat glass can be manufactured from different glass materials. For example, the prior art describes the use of the float process to manufacture mirror glass, such as borosilicate glass or aluminosilicate glass, for example, in addition to conventional soda lime glass.

Soda lime glasses are defined as glass that is manufactured essentially from the raw materials silicon dioxide (SiO_2), lime (CaCO_3) and soda (Na_2CO_3). Soda lime float glass can thereby also be thermally prestressed and thus meets the requirements for

19690405 040901

Soda lime glass can also be chemically prestressed.

The ion exchange is generally performed using alkali atoms, either in fused salts or by means of applied pastes. One conventional treatment uses potassium atoms that replace sodium atoms in the glass. One essential requirement is that the treatment take place below the transformation temperature of the glass, because otherwise the compression stress decreases significantly because of the heat. Chemically hardened glass of this type is used for special applications, such as in the aviation and aerospace industries, for centrifuge glass and in the lighting sector.

2

7% and 15% boron oxide. On account of its composition, it has a high temperature resistance and a very high hydrolytic and acid resistance. Like soda lime glass, it can be floated and thermally prestressed and is fined during manufacture using NaCl. Borosilicate float glass is therefore used in applications that require increased chemical resistance and increased temperature stability, or heat resistance.

Aluminosilicate glass is a silicate glass that has as its essential component aluminum trioxide as well as other oxides. This category includes glass from the LiO_2 - Al_2O_3 - SiO_2 system. A glass of this type can also be floated and thermally prestressed, and can be fined with SnO_2 , for example. Aluminosilicate float glass also has an improved chemical resistance and higher temperature stability, and also has the advantage that it is free of alkali components, which makes it suitable for use as a substrate glass in display technologies.

It is generally known that aluminosilicate glass from the LiO_2 - Al_2O_3 - SiO_2 system can be converted into glass ceramics with high quartz mixed crystals or keatite mixed crystals as the principal crystal phases. Glass ceramic therefore consists of a crystal phase and a residual glass phase. The initial glass is obtained by normal glass manufacturing methods. After melting and fining, the glass conventionally undergoes a hot forming by rolling, casting or pressing. Then the glass is subjected to a heat treatment, as a result of which the glass is partly transformed under controlled conditions into a fine-grain crystal phase.

A key characteristic of these glass ceramics is that they can be used to manufacture materials that, in the temperature region of room temperature to about 700°C , have an extremely low coefficient of thermal expansion $\alpha_{20/700} < 1.5 \times 10^{-6}/\text{K}$. These glass ceramics are therefore used in transparent form, for example for fireproof glass, as view windows in stoves and furnaces or as

09029409-040901

cookware, as well as for substrate material for wafer stages or mirrors for telescopes. The transparent glass ceramics can be colored dark by the addition of colored oxides. This dark coloration is desirable, for example, when the glass is used as a cooking surface, to conceal the technical components that are installed underneath the cooking surface.

In the large-scale industrial manufacture of glass ceramics, arsenic oxide and/or antimony oxide are generally used as fining agents. These fining agents are compatible with the required glass ceramic characteristics and result in good seed, or bubble, qualities or low numbers of seeds, or bubbles, in the melt. Even if these substances are incorporated into the structure of the glass, they have disadvantages from the point of view of safety and environmental protection, because special precautionary measures have to be taken during the production and preparation of the raw material on account of evaporation from the melt, as well as during post-processing, recycling and disposal.

It is known that the manufacture of glass ceramic products occurs in different stages. After the melting and the hot forming, the material is conventionally cooled to below the transformation temperature of the glass. The initial glass is then converted by controlled crystallization into the glass ceramic article. This ceramization takes place in a two-stage temperature process, in which first, by nucleus formation, at a temperature between 600°C and 800°C nuclei are generated, conventionally from ZrO_2 - TiO_2 mixed crystals. During the subsequent temperature increase, the high-quartz mixed crystals form on these nuclei at the crystallization temperature of approximately 800 to 900°C. The transformation into the keatite mixed crystals takes place in a temperature region from about 900°C to 1200°C. As a rule, glass ceramics with keatite mixed crystals as the principal phases are translucent or opaque with a white color and a slightly higher coefficient of thermal

105040-50462850

expansion than glass ceramics that have high quartz mixed crystals as the principal phase.

To simplify the manufacture of such glass ceramics with an initial float glass, attempts have been made, as described in US 3,804,608, for example, to perform the ceramization as early as in the float bath, to thereby obtain the glass ceramics directly during the float process. However, a temperature gradient over the thickness of the glass strip is produced by the hot float bath and the cold top surface of the glass, which results in crystals that grow aspherically perpendicular to the surface. As a result of the crystallization during the float process, a number of disruptive mechanical and magnetic anisotropies of characteristics are generated.

GB 1 383 201 further describes the floating of $\text{Li}_2\text{O} - \text{Al}_2\text{O}_3 - \text{SiO}_2$ glass ceramics with TiO_2 , ZrO_2 or P_2O_5 as nucleation agents, which are crystallized by the temperature control during the floating on the molten unwetted metal (tin). This publication describes the necessary temperature control in the float, namely first a rapid cooling followed by a temperature increase, to first perform nucleus formation and then crystallization. In the float, to achieve the high heating and cooling rates, vertical separations extend from the ceiling of the float bath to just above the glass, to separate different temperature zones like individual compartments. The different zones are heated in the tin bath and above the glass strip. Because this publication relates primarily to the manufacture of the floated glass ceramic and not to the unceramized glass that is poured onto the float bath as such, this prior art publication contains no reference to any undesirable surface defects in the glass during the floating. Because the teaching of this prior art patent is limited to the crystallization of the glass that is still in the float, the problem of the formation of undesirable crystals in the glass is not discussed. During the manufacture of float glass from the

TOP SECRET

Li₂O - Al₂O₃ - SiO₂ system, however, disruptive surface defects occur in the glass and have an adverse effect on the surface quality, as will be described in greater detail below. On account of the economic advantages that can be achieved, moreover, it is also necessary with a glass composition in the Li₂O - Al₂O₃ - SiO₂ system to manufacture thermally prestressed glass and to realize applications based on it. However, this type of manufacture is not possible with the glass ceramic product described in the above referenced GB patent.

OBJECT OF THE INVENTION:

The object of the invention is to provide flat float glass that can be prestressed or transformed into a glass ceramic with high quartz mixed crystals or keatite mixed crystals as the principal crystal phase, which glass:

- has no or minimal surface defects that interfere with the use of the glass and occur during floating as a result of interaction between the molten glass and the molten metal,
- can be manufactured with a high degree of light transmittance without any or minimal undesirable coloration, or discoloration,
- has a high temperature stability after thermal prestressing,
- has the required seed quality, or low number of bubbles, without the conventional fining agents such as arsenic oxide and/or antimony oxide, and which
- during the transformation to the crystal phase results in a glass ceramic that has the high surface quality of float glass and a very low coefficient of thermal expansion,
- and can be manufactured as glass ceramics in various realizations, transparent with a high light transmittance, translucent, opaque and even colored by the addition of coloring components.

SUMMARY OF THE INVENTION:

The invention teaches that this object is accomplished by a

These types of glass are therefore characterized by a composition that makes it possible to prevent the formation of undesirable surface defects during floating. Floats conventionally consist of the melting furnace, or hot end, in which the glass is melted and fined, or refined, an interface that provides the transition from the oxide atmosphere in the melting chamber into the reducing atmosphere in the rest of the system, and the float portion, in which the glass is shaped by pouring it onto a molten metal, generally Sn, in a reducing atmosphere of forming gas. The glass is formed by allowing it to flow out smoothly onto the Sn bath and by top rollers that exert a force on the surface of the glass. During the transport on the metal bath, the glass cools, and at the end of the float portion it is lifted off and transferred into a cooling furnace, or lehr, annealing furnace/oven. During the formation of the glass surface

If the glass contains more than 300 ppb Pt or more than 30 ppb Rh in dissolved form, metallic precipitations of Pt or Rh particles can form in the glass surface as a result of the reducing conditions, and these particles can serve as effective nucleation agents for large high quartz, or beta quartz, mixed crystals up to 100 μ m, and thus cause undesirable surface crystallization. These materials are used in, among other things, electrodes, linings, agitators, transport tubes, valve gates etc. Therefore, to prevent the formation of surface crystals in plants for the performance of the method for the manufacture of the glass ceramic described above, components that contain Pt or Rh are completely avoided, and/or are replaced by ceramic materials, or the conditions in the melting chamber or interface are controlled so that the above-mentioned concentrations are not exceeded.

8

components, such as from a partial reduction of the Ti^{4+} to Ti^{3+} , for example. It is therefore appropriate to keep the initial value of ZnO in the glass low from the start.

The concentration of SnO_2 in the glass is restricted to less than 1 wt.%. As a result of the action of the reducing conditions in the float portion, the SnO_2 is partly reduced, especially in the surface of the glass. Surprisingly, small metal Sn spheres having a size of about 100 nm form in the glass in the immediate surface of the glass, and although they can easily be removed during cooling or cleaning, they leave behind spherical holes, or pits, depressions, that are extremely undesirable for the intended use of the glass. These small spheres can be prevented if the concentration of SnO_2 is very low.

The above mentioned primary glasses are fined, or refined, without using the fining agents arsenic oxide and/or antimony oxide which are conventionally used to manufacture glass from the $Li_2O - Al_2O_3 - SiO_2$ system. Under the action of the reducing conditions during floating, the above mentioned fining agents in particular are reduced directly on the surface of the glass and form undesirable and visible metallic coatings. The removal of these coatings, which are aesthetically and toxicologically undesirable, requires grinding and polishing and is disadvantageous for economic reasons. To prevent the formation of the coatings, it is therefore appropriate to achieve a low seed number, or number of seeds, number of bubbles, by adding at least one alternative chemical fining agent, such as SnO_2 , CeO_2 , sulfate compounds and/or chloride compounds, for example, preferably 0.2 - 0.6 wt.% SnO_2 , to the molten glass. Alternatively, the molten glass can also be fined physically, e.g. by means of underpressure or by means of high temperature > 1750°. Thus the required seed quality, or number of bubbles, can be achieved by means of alternative fining agents and/or alternative fining methods.

09029409 040501

The oxides Li_2O , Al_2O_3 and SiO_2 in the preferred limits indicated in the claims are necessary components in the high quartz and keatite mixed crystal phase for the transformation of the glass into glass ceramic. MgO , ZnO and P_2O_5 can be incorporated as additional components. Li_2O concentrations of more than 5 wt.% increase the crystal growth rate and result in an undesirable devitrification during the manufacturing process. Because the ZnO concentration is restricted to less than 1.5 wt.% and preferably less than 1 wt.% on account of the problem of evaporation described above and the formation of a crystal band, at least 0.1 wt.% and preferably at least 0.3 wt.% MgO are necessary, so that in addition to the Li_2O , an additional component can be used for charge compensation for the Al incorporated into the crystal instead of the Si. Higher concentrations of MgO than 2.2 wt.% result in an unacceptable increase in the coefficient of thermal expansion of the glass ceramic. To prevent high viscosities of the glass and a tendency to undesired crystallization of mullite, the Al_2O_3 concentration is restricted to 25 wt.%. The SiO_2 concentration is limited to a maximum of 69 wt.%, because higher concentrations of these components sharply increase the viscosity of the glass and are thus unacceptable for the melting of the glass and with regard to the temperature stability of the float. The addition of the alkalis Na_2O , K_2O and the earth alkalis CaO , SrO and BaO of course improve the meltability, or fusability, refractoriness, and the devitrification action of the glass during floating. The concentrations are limited, however, because these components essentially remain in the residual glass phase of the glass ceramic and unacceptably increase the thermal expansion. Higher concentrations can also have an adverse effect on the

crystallization behavior. The sum of the alkalis Na_2O and K_2O should be at least 0.2 wt.% and preferably at least 0.4 wt.%. The addition of P_2O_5 can be up to 3 wt.% and is favorable for the suppression of the undesirable mullite crystallization. The concentration should be less than 3.0 wt.%, and preferably less than 2 wt.%, because P_2O_5 has an undesirable effect on acid resistance. The concentrations of the nucleation agent components TiO_2 , ZrO_2 and SnO_2 must be controlled within relatively narrow limits. On the one hand, minimum concentrations of 2.5 wt.%, and preferably 3.0 wt.% are necessary to generate nuclei in high density during the nucleation, so that transparent glass ceramics can be realized after the high quartz mixed crystals have grown. As a result of the high nuclear density, the average crystallite size of the high quartz mixed crystals remains limited to < 100 nm, as a result of which undesirable light scatter is prevented. Higher nucleation agent concentrations than 5.0 wt.%, however, under the time/temperature conditions of the float, already result in undesirable surface crystals in contact between the glass and the tin bath. If a coloring of the glass or glass ceramic materials is desired, conventional coloring components such as vanadium, chromium, manganese, iron, cobalt, copper, nickel, selenium and/or chloride compounds can be added to the glass during fusion.

The water content of the glass claimed by the invention depends on the selection of the raw materials and on the process conditions during the fusion and is conventionally between 0.01 and 0.06 Mol/liter.

The glass claimed by the invention, in a first embodiment, thereby has a composition in per cent by weight on an oxide basis

of:	
Li_2O	3.2-5.0
Na_2O	0-1.5
K_2O	0-1.5
$\Sigma\text{Na}_2\text{O}+\text{K}_2\text{O}$	0.2-2.0

MgO	0.1-2.2
CaO	0-1.5
SrO	0-1.5
BaO	0-2.5
ZnO	0-<1.5
Al ₂ O ₃	19-25
SiO ₂	55-69
TiO ₂	1.0-5.0
ZrO ₂	1.0-2.5
SnO ₂	0-<1.0
ΣTiO ₂ +ZrO ₂ +SnO ₂	2.5-5.0
P ₂ O ₅	0-3.0

In a second embodiment, the glass in one particularly preferred embodiment has a composition, in wt.% on an oxide basis, of:

Li ₂ O	3.5-4.5
Na ₂ O	0.2-1.0
K ₂ O	0-0.8
ΣNa ₂ O+K ₂ O	0.4-1.5
MgO	0.3-2.0
CaO	0-1.0
SrO	0-1.0
BaO	0-2.5
ZnO	0-1.0
Al ₂ O ₃	19-24
SiO ₂	60-68
TiO ₂	1.0-2.0
ZrO ₂	1.2-2.2
SnO ₂	0-0.6
ΣTiO ₂ +ZrO ₂ +SnO ₂	3.0-4.5
P ₂ O ₅	0-2.0.

In other words, the glass claimed by the invention, in a first embodiment, thereby has a composition in per cent by weight on an oxide basis of: Li₂O: 3.2-5.0 percent, Na₂O: 0-1.5 percent, K₂O: 0-1.5 percent, Σ Na₂O+K₂O: 0.2-2.0 percent, MgO: 0.1-2.2 percent, CaO: 0-1.5 percent, SrO: 0-1.5 percent, BaO: 0-2.5 percent, ZnO: 0-<1.5 percent, Al₂O₃: 19-25 percent, SiO₂: 55-69 percent, TiO₂: 1.0-5.0 percent, ZrO₂: 1.0-2.5 percent, SnO₂: 0-<1.0 percent, Σ TiO₂+ZrO₂+SnO₂: 2.5-5.0 percent, and P₂O₅: 0-3.0 percent.

In the second embodiment, the glass in one particularly

preferred embodiment has a composition, in wt.% on an oxide basis, of: Li_2O : 3.5-4.5 percent, Na_2O : 0.2-1.0 percent, K_2O : 0-0.8 percent, $\Sigma \text{Na}_2\text{O} + \text{K}_2\text{O}$: 0.4-1.5 percent, MgO : 0.3-2.0 percent, CaO : 0-1.0 percent, SrO : 0-1.0 percent, BaO : 0-2.5 percent, ZnO : 0-1.0 percent, Al_2O_3 : 19-24 percent, SiO_2 : 60-68 percent, TiO_2 : 1.0-2.0 percent, ZrO_2 : 1.2-2.2 percent, SnO , 0-0.6 percent, $\Sigma \text{TiO}_2 + \text{ZrO}_2 + \text{SnO}_2$: 3.0-4.5 percent, and P_2O_5 : 0-2.0 percent.

It has further been found to be advantageous that the glass compositions claimed by the invention can also be prestressed chemically, if the sum of the concentrations of Li_2O and Na_2O is greater than 3.5 wt.%. As a result of the comparatively high Li_2O concentration, it is possible to produce high compression stresses in the glass surface by ion exchange with Na_2O , preferably with K_2O .

The crystal bands that are formed with the participation of the ZnO (as described) are also caused by the additional component TiO_2 . It is assumed that in the vicinity of the surface there is a partial reduction of the titanium to the trivalent form Ti^{3+} which, by interaction with the Zn^{2+} , above a certain minimum amount of zinc, causes the crystal bands. The harmful surface crystal band can be prevented in one realization of the invention if the expression (in wt.%) $3.2 \times \text{ZnO} + \text{TiO}_2 < 4.3$ is valid. It is also possible, by reducing the amount of TiO_2 added, to partly compensate for the harmful effect of the ZnO . The formation of the crystal band is reliably prevented in preferred compositions that contain no ZnO .

The particular economic advantage of the glass composition range described above is that using the same composition, both thermally and chemically prestressable glass and glass ceramics with low coefficients of thermal expansion can be manufactured.

Expensive and time-consuming remelting between different compositions can therefore be eliminated. The manufacturing

logistics are also simplified in terms of the quantities of raw materials and cullet that have to be kept in inventory. The glass in inventory can be processed to make the different products on the basis of market demand.

For the use of the glass, e.g. as thermally prestressed fireproof glass, a high light transmittance is typically required. Any coloration in the vitrified state that interferes with the transmission of light must be avoided. For example, the applicable EN standard for the use of fireproof glass in construction requires a light transmittance for a 4 mm thickness of > 90%. It has been shown that the required light transmittance of > 89%, preferably > 90%, can be achieved in one embodiment of the invention by concentrations of less than 200 ppm Fe_2O_3 , and less than 2.5 wt.% TiO_2 in the glass.

The environmental concerns that relate to the chemical fining agents arsenic oxide and antimony oxide also apply to barium oxide, although to a lesser extent. Raw materials that contain barium, in particular if they are water-soluble such as barium chloride and barium nitrate, for example, are toxic and require special precautionary measures during use and handling. In the glass compositions claimed by the invention, it is advantageously possible to eliminate the use of BaO , except for technically unavoidable trace amounts.

During the transformation of the initial glass claimed by the invention into glass ceramics with high quartz or keatite mixed crystals as the principal crystal phase, it is therefore possible to take advantage of the high surface quality achieved during floating for glass ceramics, too, instead of the conventional rolling. Shaping by means of the float has the additional advantage over rolling that larger strip widths are possible, and the thickness can be adjusted more quickly and within wider limits.

The glass claimed by the invention is typically

105040 60462850

characterized by a coefficient of thermal expansion $\alpha_{20/300}$ between 3.5 and $5.0 \times 10^{-6}/K$. If the coefficient of thermal expansion is less than $3.5 \times 10^{-6}/K$, it is difficult to achieve sufficient prestress using conventional air prestressing systems for the breaking into pellet-like pieces required by DIN 1249. A thermal prestressing, for example, by immersion in oil-coated water, is described by the prior art, but it is technically more complex and is significantly more expensive than quenching with air in conventional air prestressing systems. To achieve a high thermal shock resistance, the coefficient of thermal expansion $\alpha_{20/300}$ should be no greater than $5.0 \times 10^{-6}/K$. The transformation temperature T_g of the float glass should be between 600 and $750^\circ C$. Such high transformation temperatures in comparison to conventional soda lime glass are positive for the achievement of a high prestressing and thus a high thermal shock resistance. The transformation temperature should not exceed $750^\circ C$, because otherwise there is a risk that in the event of a fire, the fireproof glazing will be destroyed by the warping steel frames, because the glass is not soft enough to absorb the thermal stresses. Moreover, the air prestressing system required for higher transformation temperatures is significantly more complex. The processing temperature V_A is less than $1350^\circ C$ (to limit the thermal load on the float bath and the evaporation of Sn).

In one preferred embodiment of the invention, the glass is characterized by a coefficient of thermal expansion $\alpha_{20/700}$ after transformation into the transparent glass ceramic with high quartz mixed crystals as the predominant crystal phase that differs by not more than 0.5 , and preferably by less than $0.15 \times 10^{-6}/K$ from zero expansion, to achieve high thermal shock resistance.

For glass ceramic materials in transparent form, e.g. for use as windows in furnaces, stoves and ovens, the concentrations should be $TiO_2 < 2$ wt.%, $SnO_2 < 0.5$ wt.% and $Fe_2O_3 < 200$ ppm, so

On transparent, translucent or opaque glass ceramics, the desired colors are achieved by the addition of the coloring compounds individually or together. In this case, even small additions will frequently suffice.

When the glass is transformed into glass ceramic with keatite mixed crystals as the predominant crystal phase, the coefficient of thermal expansion should be less than $1.5 \times 10^{-6}/K$. Such glass ceramics can be transparent, white translucent or white opaque, depending on the composition. When coloring oxides are used, the white color is correspondingly over-dyed, or cross-dyed, over-colored.

The glass is melted in a melting furnace in a conventional atmosphere containing oxygen from raw materials that are conventional in the glass industry, and subjected to a fining process to eliminate the bubbles. The melt flows through a block with a flow opening and through an interface that keeps it away from the atmosphere that contains the oxygen. In the interface the melt is agitated and transported via a trough into the float,

The flat float glass claimed by the invention can be used preferably both as thermally prestressable glass and, after conversion into a glass ceramic with high quartz mixed crystals or keatite mixed crystals as the principal crystal phase, as a glass ceramic claimed by the invention with a low coefficient of thermal expansion. The thermally prestressable glass is used preferably as thermally prestressed fireproof glass with safety glass characteristics in accordance with DIN 1249 (breakage into pellets). The glass ceramic claimed by the invention is preferably used in transparent form as fireproof glass, for windows in furnaces and ovens, as covers for high-energy lights and as windows for pyrolysis ovens, and in dark colored form as heating plates for cooling and grilling. By applying a light-absorbing coating on the underside, transparent glass ceramics can be used to manufacture a cooking surface with the required light transmittance.

NHL: ktp/smj

Transparent glass ceramic can be used as fireproof glass without the need for expensive polishing of the surface. When the glass ceramic is used in windows for furnaces, ovens or pyrolysis ovens and as a covering for high-energy lights, the surface produced by the float process is significantly less sensitive to the adherence of dirt and can be cleaned more easily than a rolled surface with its microroughness.

The above-discussed embodiments of the present invention will be described further hereinbelow. When the word "invention" is used in this specification, the word "invention" includes "inventions", that is the plural of "invention". By stating "invention", the Applicant does not in any way admit that the present application does not include more than one patentably and non-obviously distinct invention, and maintains that this application may include more than one patentably and non-obviously distinct invention. The Applicant hereby asserts that the disclosure of this application may include more than one invention, and, in the event that there is more than one invention, that these inventions may be patentable and non-obvious one with respect to the other.

BRIEF DESCRIPTION OF THE TABLES

This invention is explained in further detail in the examples presented below.

Table 1 presents compositions and characteristics of different types of float glass for several exemplary embodiments. Examples 1 to 14 are types of glass as claimed by the invention and Examples 15 to 17 are comparative examples that are not part of this invention.

Table 2 presents the characteristics of the corresponding glass ceramics.

DESCRIPTION OF THE PREFERRED EMBODIMENT

The initial glasses in Table 1 were melted and fined using raw materials that are conventional in the glass industry. The

09829409 "040901
T0404" 646266

Fe₂O₃ content of these glasses is 160 ppm. In Example 2, a level of 100 ppm Fe₂O₃ was achieved by using a pure SiO₂ raw material. The glass in Examples 1-16 was melted and fined in pots made of fused quartz, or silica glass, at temperatures of approximately 1620°C. Then the melts were transferred to a platinum/rhodium pot with an inner pot made of fused quartz to prevent direct contact with the platinum/rhodium, and homogenized at temperatures of approximately 1580°C for 30 minutes. After dead-melting, or killing, at approximately 1640°C for 1 hour, castings approximately 140 x 100 x 30 mm were poured and cooled from approximately 660°C to room temperature in a cooling furnace, or lehr, annealing furnace. The test specimens, e.g. bars for measurement of the transformation temperature T_g and of the coefficient of thermal expansion $\alpha_{20/300}$, were prepared from these castings. As a result of the avoidance of contact between the glass melt and the platinum/rhodium, the Pt content was 10-30 ppb, and the rhodium content was below the limit of detection, i.e. < 10 ppb.

The compositions claimed by the invention were melted in a high-frequency heated 4 liter pot made of sintered fused quartz, or silica glass, at temperatures of approximately 1750°C. After the glass had been completely melted, it was fined for 1 hour at 1900-2000°C. This high-temperature fining produced castings that were very bubble-free. These castings were prepared for tests for pouring into a commercial float used to manufacture special glass. The castings were remelted in a 2 liter pot made of platinum/rhodium with a fused quartz inner pot. These pots were fastened to the front end of a suspension apparatus with a long rod. The suspension apparatus with the pot was introduced into the float via small openings. The melt in the pot was poured onto the molten tin at the beginning of the float, behind the spout lip, and as it was flowing it was attached to the production strip which consisted of borosilicate glass. The hold time of the

05829409 040901
106040 60452860

09023409 040301
poured glass on the float bath was approximately 30-40 minutes. The test melts were transported through the float and through the cooling furnace together with the borosilicate production strip. Behind the cooling furnace, the solidified test melts, which were approximately 4-6 mm thick, were cut off the production strip and removed for testing. As a result of the very similar coefficients of thermal expansion of borosilicate glass and the compositions claimed by the invention, the test melts also adhered to the borosilicate glass very well, and the test melts did not break off the production strip as a result of stresses caused by different coefficients of thermal expansion. The floated compositions claimed by the invention were measured for their light transmittance in accordance with DIN 5033. The floated test melts were also inspected on their upper and lower sides for glass defects, in particular for crystals. The upper side of the floated test melts was free of crystals. Only in isolated cases, when substances from the cover of the float bath fell onto the glass melt, were crystals formed by contact. On the underside of the floated test melts there were isolated but not visually unacceptable crystals. The origin of these crystals was traced to the penetration of small quantities of atmospheric oxygen into the float bath at the boundary between the test melts and the molten tin bath. The atmospheric oxygen that entered under the test conditions caused local oxidation of the Sn, which then diffused into the glass and acted as nucleation agents for the generation of local high quartz mixed crystals. The thermal prestressability of the glass and the transformation into glass ceramic were not adversely affected by the isolated crystals on the underside.

No precipitations of Pt and Rh in particular were found.

The very damaging crystal bands did not occur in the test melts with the glass compositions claimed by the invention.

Nor were any Sn drops found on the upper side of the floated

test melts.

Comparative Example No. 15 shows a composition that was melted with As_2O_3 as the fining agent. Castings of this composition were poured into the float using the method described above and attached to the production strip. The float glass removed from the float showed metallic coatings, or stripes, of arsenic, which were formed by the reducing forming gas atmosphere of the float bath. In contrast to Comparative Example No. 15, Comparative Example No. 16 used the same basic composition but there was no addition of As_2O_3 . After the glass was poured onto the float bath, the undesirable crystal band of high quartz mixed crystals was found on both sides near the surface. This glass has a composition with a high ZnO concentration and a relatively high TiO_2 concentration.

In Comparative Example 17, the composition from Example 16 was melted directly in a platinum/rhodium pot without the inner fused quartz pot. The platinum content of the molten castings was measured at 900 ppb. The float glass had dendritically grown surface crystals up to a size of 100 μm and adjacent droplet-shaped metallic crystallizations.

The transformation into the glass ceramic occurs under the nucleation and crystallization conditions listed in Table 2. Following a rapid heating to 600°C, the glass is heated to the nucleation temperature, and then from the nucleation temperature to the crystallization temperature at a uniform heating rate of 2.5 K/min. The glass is then cooled from the maximum temperature to approximately 600°C at a cooling rate of approximately 4 K/min., followed by the deactivation of the furnace heater. Example 11 shows a glass ceramic that was transformed by an additional temperature increase to 1100°C for 1 hour into a white translucent glass ceramic with keatite mixed crystals as the predominant crystal phase. The rest of the examples as claimed by the invention, as a result of their concentration of high quartz

One feature of the invention resides broadly in a flat float glass that can be prestressed or transformed into a glass ceramic with high quartz mixed crystals or keatite mixed crystals, that has a concentration of less than 300 ppb Pt, less than 30 ppb Rh, less than 1.5 wt.% ZnO and less than 1 wt.% SnO₂ to prevent undesirable surface defects during floating, and that is refined during melting without the use of the conventional fining agents arsenic oxide and/or antimony oxide.

Yet another feature of the invention resides broadly in a flat glass characterized by a composition (in wt.% on an oxide basis) of: Li_2O : 3.5-4.5 percent, Na_2O : 0.2-1.0 percent, K_2O : 0-0.8 percent, $\Sigma \text{Na}_2\text{O} + \text{K}_2\text{O}$: 0.4-1.5 percent, MgO : 0.3-2.0 percent, CaO : 0-1.0 percent, SrO : 0-1.0 percent, BaO : 0-2.5 percent, ZnO : 0-1.0 percent, Al_2O_3 : 19-24 percent, SiO_2 : 60-68 percent, TiO_2 : 1.0-2.0 percent, ZrO_2 : 1.2-2.2 percent, SnO_2 : 0-0.6 percent, $\Sigma \text{TiO}_2 + \text{ZrO}_2 + \text{SnO}_2$: 3.0-4.5 percent, P_2O_5 : 0-2.0, optionally with the addition of coloring components such as V, Cr, Mn, Fe,

Co, Cu, Ni, Se and/or Cl compounds.

Still another feature of the invention resides broadly in a flat glass characterized by the fact that the sum $\text{Li}_2\text{O} + \text{Na}_2\text{O} > 3.5 \text{ wt.}\%$ and the glass can therefore be chemically prestressed.

A further feature of the invention resides broadly in a flat glass characterized by the fact that to prevent the formation of an undesirable crystal band near the surface during floating, the following expression (in wt.%) is valid: $3.2 \times \text{ZnO} + \text{TiO}_2 \leq 4.3$.

Another feature of the invention resides broadly in a flat glass characterized by concentrations of less than 200 ppm Fe_2O_3 and less than 2.5 wt.% TiO_2 to counteract undesired coloration in the vitrified state and to achieve a light transmittances at a thickness of 4 mm of $> 89\%$ and preferably $> 90\%$.

Yet another feature of the invention resides broadly in a flat glass characterized by the fact that the glass is technically, or industrially, free of ZnO and BaO.

Still another feature of the invention resides broadly in a flat glass characterized by a coefficient of thermal expansion $\alpha_{20/300}$ between 3.5 and $5.0 \times 10^{-6}/\text{K}$, a transformation temperature T_g between 600 and 750°C and a processing temperature V_A below 1350°C .

A further feature of the invention resides broadly in a flat glass characterized by the fact that the glass ceramic manufactured by transformation has a transparent, translucent or opaque appearance, and has an additional color when coloring components are added.

Another feature of the invention resides broadly in a flat glass characterized by a coefficient of thermal expansion $\alpha_{20/700}$ after transformation into the glass ceramic with keatite mixed crystals as the predominant crystal phase of less than $1.5 \times 10^{-6}/\text{K}$.

Yet another feature of the invention resides broadly in a flat glass characterized by a coefficient of thermal expansion

05029409 040904
FOUO 6062250

$\alpha_{20/700}$ after transformation into the glass ceramic with high quartz mixed crystals as the predominant crystal phase of $(0 \pm 0.5) \times 10^{-6}/K$, preferably $(0 \pm 15) \times 10^{-6}/K$.

Still another feature of the invention resides broadly in a flat glass characterized by the fact that the transparent glass ceramic, to achieve a light transmittance at 4 mm thickness of > 80%, contains less than 2 wt.% TiO_2 , less than 0.5 wt.% SnO_2 and less than 200 ppm Fe_2O_3 .

A further feature of the invention resides broadly in a flat glass characterized by the fact that the glass ceramic is colored with V, Cr, Mu, or Mn, Fe, Co and/or Ni compounds with a light transmittance of < 5% at a thickness of 4 mm.

Another feature of the invention resides broadly in a flat glass as claimed characterized by the fact that to achieve a low number of bubbles, or seeds, at least one alternative chemical fining agent such as SnO_2 , CeO_2 , sulfate compounds, chloride compounds for example, preferably 0.2 - 0.6 wt.% SnO_2 is added to the glass melt.

Yet another feature of the invention resides broadly in a flat glass characterized by the fact that to achieve a low number of bubbles, the glass melt is physically fined, e.g. by under pressure or by means of high temperature > 1750°C.

The components disclosed in the various publications, disclosed or incorporated by reference herein, may be used in the embodiments of the present invention, as well as equivalents thereof.

The appended drawings in their entirety, including all dimensions, proportions and/or shapes in at least one embodiment of the invention, are accurate and are hereby included by reference into this specification.

All, or substantially all, of the components and methods of the various embodiments may be used with at least one embodiment or all of the embodiments, if more than one embodiment is

106040-040301

All of the patents, patent applications and publications recited herein, and in the Declaration attached hereto, are hereby incorporated by reference as if set forth in their entirety herein.

Another foreign patent publication application, namely, Federal Republic of Germany Patent Application No. DE 100 17 698.4-45, filed on April 8, 2000, having inventors Dr. Sabine MELSON, Dr. K. SCHAUPERT, and Dr. Peter NASS, entitled, "Reinigungsfreundlicher Glaskeramikkörper," and DE-OS 100 17 698.4-45 and DE-PS 100 17 698.4-45, as well as their published equivalents, and other equivalents or corresponding applications, if any, in corresponding cases in the Federal Republic of Germany and elsewhere, and the references cited in any of the documents cited herein, are hereby incorporated by reference as if set forth in their entirety herein.

25

and DE-OS 100 17 699.2-45 and DE-PS 100 17 699.2-45, as well as their published equivalents, and other equivalents or corresponding applications, if any, in corresponding cases in the Federal Republic of Germany and elsewhere, and the references cited in any of the documents cited herein, are hereby incorporated by reference as if set forth in their entirety herein.

A further foreign patent publication application, namely, Federal Republic of Germany Patent Application No. DE 100 17 696.8-33, filed on April 8, 2000, having inventors Dr. Sabine MELSON and Dr. Peter NASS, entitled, "Transparente Abdeckung der Strahlungsquelle von Lampen," and DE-OS 100 17 696.8-33 and DE-PS 100 17 696.8-33, as well as their published equivalents, and other equivalents or corresponding applications, if any, in corresponding cases in the Federal Republic of Germany and elsewhere, and the references cited in any of the documents cited herein, are hereby incorporated by reference as if set forth in their entirety herein.

The details in the patents, patent applications and publications may be considered to be incorporable, at applicant's option, into the claims during prosecution as further limitations in the claims to patentably distinguish any amended claims from any applied prior art.

The following U.S. Patent Application is hereby incorporated by reference as if set forth in its entirety herein as follows: U.S. Patent Application No. _____, having attorney docket No. NHL-FMW-01 US (SCT), having inventors Dr. Sabine MELSON, Dr. K. SCHAUPERT, and Dr. Peter NASS, filed on April 6, 2001, claiming priority from Federal Republic of Germany Patent Application No. DE 100 17 698.4-45, filed on April 8, 2000, having inventors Dr. Sabine MELSON, Dr. K. SCHAUPERT, and Dr. Peter NASS, entitled, "Reinigungsfreundlicher Glaskeramikkörper," is hereby incorporated by reference as if set forth in its entirety herein.

092240 040901

The following U.S. Patent Application is hereby incorporated by reference as if set forth in its entirety herein as follows:
U.S. Patent Application No. _____, having attorney docket No. NHL-FMW-03 US (SCT), having inventors Dr. Sabine MELSON and Stefan HUBERT, filed on April 6, 2001, claiming priority from Federal Republic of Germany Patent Application No. DE 100 17 699.2-45, filed on April 8, 2000, having inventors Dr. Sabine MELSON and Stefan HUBERT, entitled "Verglasung von gegenüber der Umgebung im Weltraum oder in Polarregionen abgekapselten Räumen," is hereby incorporated by reference as if set forth in its entirety herein.

The following U.S. Patent Application is hereby incorporated by reference as if set forth in its entirety herein as follows:
U.S. Patent Application No. _____, having attorney docket No. NHL-FMW-04 US (SCT), having inventors Dr. Sabine MELSON and Dr. Peter NASS, filed on April 6, 2001, claiming priority from Federal Republic of Germany Patent Application No. DE 100 17 696.8-33, filed on April 8, 2000, having inventors Dr. Sabine MELSON and Dr. Peter NAB, entitled, "Transparente Abdeckung der Strahlungsquelle von Lampen," is hereby incorporated by reference as if set forth in its entirety herein.

U.S. Pat. No. 3,804,608 issued to Gaskell et al. on April 16, 1974 and entitled "Method for making glass ceramic materials"; and U.S. Pat. No. 3,809,543 issued to Gaskell et al. on May 7, 1974 and entitled "Method of making glass ceramic materials on molten metal support, which corresponds, inter alia, to GB Patent No. 1,383,201, are hereby incorporated by reference as if set forth in their entirety herein.

The term DIN refers to the standards of the German Standards Association, Deutsches Institut für Normung.

The term EN refers to European standards.

The expression thermal expansion coefficient or coefficient of thermal expansion ($\alpha_{20/300}$) in at least one embodiment of the

invention is to mean: a thermal coefficient (α) as possibly nominally applicable in the temperature range of nominal from about 20 to about 300 (in the Celsius and/or Kelvin scale, as possibly applicable) in the context of the indicated data.

The expression glass transition temperature or transformation temperature (T_g) in at least one embodiment of the invention is to mean: (1) the temperature below which a substance becomes superconducting; or (2) the temperature at which one polymorph changes into the next thermodynamically stable state; as the shown technical data suggest.

In accordance with one possible embodiment the glass composition comprises in weight percent based on oxide: Li_2O three point two to five point zero percent and within the range percentages in tenth of percent steps such that any tenth of a percent may be a limit of a diminished range; Na_2O zero to one point five percent and within the range percentages in tenth of percent steps such that any tenth of a percent may be a limit of a diminished range; K_2O zero to one point five percent and within the range percentages in tenth of percent steps such that any tenth of a percent may be a limit of a diminished range; $\Sigma\text{Na}_2\text{O}+\text{K}_2\text{O}$ point two to two point zero percent and within the range percentages in tenth of percent steps such that any tenth of a percent may be a limit of a diminished range; MgO point one to two point two percent and within the range percentages in tenth of percent steps such that any tenth of a percent may be a limit of a diminished range; CaO zero to one point five percent and within the range percentages in tenth of percent steps such that any tenth of a percent may be a limit of a diminished range; SrO zero to one point five percent and within the range percentages in tenth of percent steps such that any tenth of a percent may be a limit of a diminished range; BaO zero to two point five percent and within the range percentages in tenth of percent steps such that any tenth of a percent may be a limit of

106040-60452850

a diminished range; ZnO zero to less than one point five percent and within the range percentages in tenth of percent steps such that any tenth of a percent may be a limit of a diminished range; Al_2O_3 , nineteen to twenty-five percent and within the range percentages in tenth of percent steps such that any tenth of a percent may be a limit of a diminished range; SiO_2 , fifty-five to sixty-nine percent and within the range percentages in tenth of percent steps such that any tenth of a percent may be a limit of a diminished range; TiO_2 , one point zero to five point zero percent and within the range percentages in tenth of percent steps such that any tenth of a percent may be a limit of a diminished range; ZrO_2 , one point zero to two point five percent and within the range percentages in tenth of percent steps such that any tenth of a percent may be a limit of a diminished range; SnO_2 , zero to less than one point zero percent and within the range percentages in tenth of percent steps such that any tenth of a percent may be a limit of a diminished range; $\Sigma\text{TiO}_2+\text{ZrO}_2+\text{SnO}_2$, two point five to five point zero percent and within the range percentages in tenth of percent steps such that any tenth of a percent may be a limit of a diminished range; P_2O_5 , zero to three point zero percent and within the range percentages in tenth of percent steps such that any tenth of a percent may be a limit of a diminished range.

In another embodiment, the glass may possible comprise: Li_2O three point five to four point five percent and within the range percentages in tenth of percent steps such that any tenth of a percent may be a limit of a diminished range; Na_2O point two to one point zero percent and within the range percentages in tenth of percent steps such that any tenth of a percent may be a limit of a diminished range; K_2O zero to point eight percent and within the range percentages in tenth of percent steps such that any tenth of a percent may be a limit of a diminished range; $\Sigma\text{Na}_2\text{O}+\text{K}_2\text{O}$ point four to one point five percent and within the

05829409 "040501
FOUO

range percentages in tenth of percent steps such that any tenth of a percent may be a limit of a diminished range; MgO point three to two point zero percent and within the range percentages in tenth of percent steps such that any tenth of a percent may be a limit of a diminished range; CaO zero to one point zero percent and within the range percentages in tenth of percent steps such that any tenth of a percent may be a limit of a diminished range; SrO zero to one point zero percent and within the range percentages in tenth of percent steps such that any tenth of a percent may be a limit of a diminished range; BaO zero to two point five percent and within the range percentages in tenth of percent steps such that any tenth of a percent may be a limit of a diminished range; ZnO zero to one point zero percent and within the range percentages in tenth of percent steps such that any tenth of a percent may be a limit of a diminished range; Al_2O_3 nineteen to twenty-four percent and within the range percentages in tenth of percent steps such that any tenth of a percent may be a limit of a diminished range; SiO_2 sixty to sixty-eight percent and within the range percentages in tenth of percent steps such that any tenth of a percent may be a limit of a diminished range; TiO_2 one point zero to two point zero percent and within the range percentages in tenth of percent steps such that any tenth of a percent may be a limit of a diminished range; ZrO_2 one point two to two point two percent and within the range percentages in tenth of percent steps such that any tenth of a percent may be a limit of a diminished range; SnO_2 zero to point six percent and within the range percentages in tenth of percent steps such that any tenth of a percent may be a limit of a diminished range; $\Sigma TiO_2 + ZrO_2 + SnO_2$ three point zero to four point five percent and within the range percentages in tenth of percent steps such that any tenth of a percent may be a limit of a diminished range; P_2O_5 zero to two point zero percent and within the range percentages in tenth of percent steps such that any tenth of a percent may be

0329409-040901

Expressed in other words, the glass composition in accordance with the present invention may comprise, in weight percent based on oxide: lithium oxide (Li_2O) in the range of from 3.2 percent to 5.0 percent; sodium oxide (Na_2O) from 0 percent to 1.5 percent; potassium oxide (K_2O) from 0 percent to 1.5 percent; the sum of sodium oxide (Na_2O) + potassium oxide (K_2O) may be in the range of from 0.2 percent to 2.0 percent; magnesium oxide (MgO) in the range of from 0.1 percent to 2.2 percent; calcium oxide (CaO) in the range of from 0 percent to 1.5 percent; strontium oxide (SrO) from 0 percent to 1.5 percent; barium oxide (BaO) may be present in the range of from 0 percent to 2.5 percent; zinc oxide (ZnO) may be present in the range of from 0 percent to less than 1.5 percent; aluminium oxide (Al_2O_3) in the range of from 19 percent to 25 percent; silicon dioxide (SiO_2) in the range of from 55 percent to 69 percent; titanium dioxide (TiO_2) in the range of from 1.0 percent to 5.0 percent; zirconium dioxide (ZrO_2) in the range of from 1.0 percent to 2.5 percent; tin dioxide (SnO_2) may be present from 0 percent to less than 1.0 percent; the sum of titanium dioxide (TiO_2) + zirconium (ZrO_2) + tin dioxide (SnO_2) may be in the range of from 2.5 percent to 5.0 percent; phosphoric oxide (P_2O_5) may be present in the range of from 0 percent to 3.0 percent. Of course, there may be present coloring agents from the group comprising compounds of: vanadium (V), chromium (Cr), manganese (Mn), iron (Fe), cobalt (Co), copper (Cu), nickel (Ni), selenium (Se) and/or chlorine (Cl).

Some examples of flat glass production which may possibly be incorporated in an example of the present invention may be found in U.S. Pat. No. 3,218,143 issued to De Lajarte on November 16, 1965 and entitled "Process for the manufacture of flat glass"; U.S. Pat. No. 3,930,826 issued to Schornhorst on January 6, 1976

Some examples relating to aluminosilicate, features of which may possibly be incorporated in an embodiment of the present invention may be found in U.S. Pat. No. 4,084,974 issued to Beall et al. on April 18, 1978 and entitled "Method of making light-absorbing glass-ceramic articles"; U.S. Pat. No. 4,530,909 issued to Makishima et al. on July 23, 1985 and entitled "Aluminosilicate glass containing Y_2O_3 concentrate and ZrO_2 "; U.S. pat. No. 4,626,515 issued to Chyung et al. on December 2, 1986 and entitled "Reinforced alkaline earth aluminosilicate glasses"; U.S. Pat. No. 4,846,866 issued to Chyung et al. on July 11, 1989 and entitled "Providing reinforced alkaline earth aluminosilicate glasses"; and U.S. Pat. No. 6,060,168 issued to Kohli on May 9, 2000 and entitled "Glasses for display panels and photovoltaic devices", all of these U.S. patents being hereby expressly incorporated by reference as if set forth in their entirety herein.

32

possibly be incorporated in an embodiment of the present invention may be found in U.S. Pat. No. 4,140,939 issued to Bonazoli et al. on February 20, 1979 and entitled "Tungsten halogen lamp for headlights"; U.S. Pat. No. 4,319,156 issued to Bienvenue et al. on March 9, 1982 and entitled "Vehicle headlight having dual filament tungsten halogen lamp"; U.S. Pat. No. 4,339,685 issued to Saguchi et al. on July 13, 1982 and entitled "Sealed beam lamp assembly"; U.S. Pat. No. 4,342,142 issued to Nieda et al. on August 3, 1982 and entitled "Method for manufacturing sealed-beam type electric bulb"; U.S. Pat. No. 4,540,911 issued to Arai et al. on September 10, 1985 and entitled "Halogen lamp unit"; U.S. Pat. No. 4,607,016 issued to Danielson et al. on August 19, 1986 and entitled "Glass for use as tungsten-halogen lamp envelopes"; U.S. Pat. No. 4,801,845 issued to Kiesel on January 31, 1989 and entitled "Halogen incandescent lamp structure"; U.S. Pat. No. 5,513,08 issued to Ho on April 30, 1996 and entitled "Ultraviolet-reduced halogen lamp"; U.S. Pat. No. 5,850,124 issued to Hasegawa et al. on December 15, 1998 and entitled "Automobile lamp bulb with welded low beam shield"; U.S. Pat. No. 5,855,430 issued to Coughaine et al. on January 5, 1999 and entitled "Vehicle headlamp assembly"; U.S. Pat. No. 5,949,181 issued to Tabata et al. on September 7, 1999 and entitled "Automotive lamp bulb with alignment bead"; U.S. Pat. No. 5,984,750 issued to Nishibori et al. on November 16, 1999 and entitled "Method of sealing halogen lamp"; and U.S. Pat. No. 6,183,113 B1 issued to Waldmann on February 6, 2001 and entitled "Halogen lamp", all of these U.S. patents being hereby expressly incorporated by reference as if set forth in their entirety herein.

Some examples relating to float glass processes, features of which may possibly be incorporated in an embodiment of the present invention may be found in U.S. Pat. No. 4,305,745 issued to Mouly on December 15, 1981 and entitled "Method of attenuating

Some examples of ceramising glass-ceramic or glass, features of which may possibly be incorporated in an embodiment of the present invention may be found in U.S. Pat. No. 4,824,463 issued to Neuhoff et al. on April 25, 1989 and entitled "Process for ceramising glass-ceramic sheets"; and U.S. Pat. No. 4,851,022 issued to Günthner on July 25, 1989 and entitled "Method and oven for ceramising glass plates", all of these U.S. patents being hereby expressly incorporated by reference as if set forth in their entirety herein.

34

Grossman on November 21, 1978 and entitled "Aluminous quartz ceramics and method"; U.S. Pat. No. 4,391,914 issued to Beall et al. on July 5, 1983 and entitled "Strengthened glass-ceramic article and method"; U.S. Pat. No. 6,197,710 B1 issued to Ōhara et al. on March 6, 2001 and entitled "Luminous glass ceramics"; and U.S. Pat. No. 6,204,211 B1 issued to Ōhara et al. on March 20, 2001 and entitled "Luminous glass ceramics", all of these U.S. patents being hereby expressly incorporated by reference as if set forth in their entirety herein.

Some examples of stressed glass, chemically stressed glass and/or processes for making stressed or chemically stressed glass, features of which may possibly be incorporated in an embodiment of the present invention may be found in U.S. Pat. No. 3,931,438, issued to Beall et al. on January 6, 1976 and entitled, "Differential Densification of Strengthening Glass-Ceramics"; U.S. Pat. No. 3,962,515, issued to Dumbaugh, Jr. et al. on June 8, 1976 and entitled, "Strengthened Composite Glass Article and Method of Production"; U.S. Pat. No. 3,997,249, issued to Krohn et al. on December 14, 1976 and entitled, "Ion Exchangeable Segment Glass"; U.S. Pat. No. 4,112,485, issued to Sutter on September 5, 1978 and entitled, "Impact Resistant Explosion Proof Lamp Comprising Encapsulated Light Source"; U.S. Pat. No. 4,287,018, issued to Gulati et al. on September 1, 1981 and entitled, "Method for Finishing Glass-Plastic Laminated Lens Blanks"; U.S. Pat. No. 4,397,669, issued to Haisma et al. on August 9, 1983 and entitled, "Method for the Precision Moulding of Glass Articles, Method of Manufacturing a Mould, and Mould for the Precision Moulding of Glass Articles"; U.S. Pat. No. 5,188,990 issued to Dumesnil et al. on February 23, 1993 and entitled, "Low Temperature Sealing Glass Compositions"; and U.S. Pat. No. 6,184,162 B1, issued to Speit et al. on February 6, 2001 and entitled, "Glasses and Glass-Ceramics with High E-Moduli," all of these U.S. patents being hereby expressly incorporated by

"0329409" 040901

reference as if set forth in their entirety herein.

Some examples of prestressable glass, prestressed glass, chemically prestressed glass and/or processes for making prestressed or chemically prestressed glass, features of which may possibly be incorporated in an embodiment of the present invention may be found in U.S. Pat. No. 3,976,898, issued to Newson on August 24, 1976 and entitled "Prestressed Glass, Aezoelectric Electrical Power Source"; U.S. Pat. No. 4,170,505, issued to Zraggen on October 9, 1979 and entitled, "Method for Making and Applying Irradiation Curable Glass Banding"; U.S. Pat. No. 4,259,118, issued to Sack on March 31, 1981 and entitled, "Thermally High Pre-Stressable Glass with High Hot Stressing Factors"; U.S. Pat. No. 4,332,241, issued to Dalstein et al. on June 1, 1982 and entitled, "Solar Energy Collector Panel"; U.S. Pat. No. 4,715,879, issued to Schmitte et al. on December 29, 1987 and entitled, "Method for the Manufacture of a Tempered and/or Curved Glass Pane with Reduced Transmission"; U.S. Pat. No. 4,781,432, issued to Zonger et al. on November 1, 1988 and entitled, "Optic Fibre Transmission Cable Reinforcement"; U.S. Pat. No. 5,846,280, issued to Speit on December 8, 1998 and entitled, "Process for Production of Chemically Prestressed Glass"; and U.S. Pat. No. 5,895,768, issued to Speit on April 20, 1999 and entitled, "Chemically Prestressable Aluminosilicate Glass and Products Made Therefrom," all of these U.S. patents being hereby expressly incorporated by reference as if set forth in their entirety herein.

Some examples of ceramic materials that may be used on chemically stressed components may be found in the following U.S. Patents: No. 5,182,411, issued to Vaahs et al. on January 26, 1993 and entitled, "Polymeric Chlorosilazanes, Process for Their Preparation, Ceramic Materials Containing Silicon Nitride Which Can Be Manufactured Therefrom, and Their Manufacture"; No. 5,189,132, issued to Vaahs et al. on February 23, 1993 and

entitled, "Polymeric Hydridochlorosilazanes, Process for Their Preparation, Ceramic Materials Containing Silicon Nitride Which Can Be Manufactured Therefrom, and Their Manufacture"; and No. 5.196,556 issued to Vaahs et al. on March 23, 1993, and entitled, "Polysubstituted Chlorine-Containing Silazane Polymers, Process for Their Preparation, Ceramic Materials Containing Silicon Nitride Which Can Be Manufactured Therefrom, and Their Manufacture."

In accordance with one aspect of the invention there is provided a flat float glass having surface defects which are minimized; said glass being configured at least as one of: (a) to be prestressable; (b) to be capable of being transformed into a glass ceramic having surficial high quartz mixed crystals or keatite mixed crystals; said glass having a minimized concentration of (c), (d), (e), and (f) to minimize surface defects on said glass; said glass comprising: (c) less than three hundred parts per billion of platinum (Pt); (d) less than thirty parts per billion of rhodium (Rh); (e) less than one point five weight percent zinc oxide (ZnO); and (f) less than one weight percent of tin dioxide (SnO₂); and said glass comprising refined glass that is refined during melting in the absence of substantially all of (i.), and (ii.): (i.) arsenic oxide; and (ii.) antimony oxide.

In accordance with another aspect the invention comprises a flat float glass having surface defects which are minimized; said glass comprising at least one of: (a) a prestressable flat float glass; (b) a glass ceramic being transformable into a glass ceramic comprising high quartz mixed crystals; and (c) a glass ceramic being transformable into a glass ceramic comprising keatite mixed crystals; said glass having a minimized concentration of (d), (e), (f), and (g) to minimize surface defects on said glass during floating thereof, said glass comprising: (d) less than three hundred parts per billion of

09329409-043901
T0540-045350

platinum (Pt); (e) less than thirty parts per billion of rhodium (Rh); (f) less than one point five weight percent zinc oxide (ZnO); and (g) less than one weight percent of tin dioxide (SnO₂); and said glass comprising refined glass; said refined glass being substantially free of all of (i.), and (ii.): (i.) arsenic oxide; and (ii.) antimony oxide.

In yet another aspect of the invention there is provided a method of making flat float glass having surface defects which are minimized, said method comprising: (A) melting and refining glass substantially or essentially or substantially in the absence of (i.) arsenic oxide; and (ii.) antimony oxide; (B) floating said glass and minimizing surface defects in said glass during floating of said glass by minimizing the concentration of (a), (b), (c), and (d) to: (a) less than three hundred parts per billion of platinum (Pt); (b) less than thirty parts per billion of rhodium (Rh); (c) less than one point five weight percent zinc oxide (ZnO); and (d) less than one weight percent of tin dioxide (SnO₂); and producing at least one of: (C1) producing a prestressable flat float glass; (C2) producing a transformable flat float glass being transformable into a glass ceramic comprising high quartz mixed crystals; and (C3) producing a transformable flat glass being transformable into a glass ceramic comprising keatite mixed crystals.

Flat glass as claimed in one of the claims may possibly be characterized by the fact that to prevent the formation of an undesirable crystal band near the surface during floating, or possibly in the flat glass the following expression (in wt.%) is valid: $3.2 \times \text{ZnO} + \text{TiO}_2 \leq 4.3$. Flat glass as claimed in one of the claims may possibly be characterized by the fact that to prevent the formation of an undesirable crystal band near the surface during floating, or possibly in the flat glass the following expression (in wt.%) is valid: $3.2 \times \text{ZnO} + \text{TiO}_2 \leq 4.3$ to minimize an undesirable crystal band near the surface of the

05029409-040901

glass.

In accordance with one aspect the invention contemplates a flat glass characterized by the fact that the glass is technically, or industrially, free of zinc oxide (ZnO) and barium oxide (BaO). The invention also comprises flat glass characterized by the fact that the glass is substantially free of ZnO and BaO. The invention also comprises flat glass characterized by the fact that the glass is virtually free of ZnO and BaO. The invention further comprises flat glass characterized by the fact that the glass is essentially free of ZnO and BaO. The invention also comprises flat glass characterized by the fact that the glass is almost free of ZnO and BaO.

In accordance with one aspect, the invention contemplates a flat glass characterized by the fact that in order to achieve a low number of bubbles, or seeds, at least one alternative chemical fining agent such as SnO_2 , CeO_2 , sulfate compounds, chloride compounds for example, preferably 0.2 - 0.6 wt.% SnO_2 is added to the glass melt. The invention also contemplates a flat glass characterized by the fact that to achieve a low number of bubbles, or seeds, at least one chemical fining agent such as SnO_2 , CeO_2 , sulfate compounds, chloride compounds for example, preferably 0.2 - 0.6 wt.% SnO_2 is added to the glass melt.

Well-known conventional fining agents, or refining agents, that may possibly be used for fining the glass of the present invention comprise arsenic (As) compounds, such as arsenic oxide, arsenic chloride, arsenic nitrate, antimony (Sb) compounds, sodium (Na) compounds, such as sodium chloride, sodium sulfate, sodium sulfite, calcium (Ca) compounds, such as calcium sulfate, barium (Ba) compounds, such as barium sulfide, potassium (K) compounds, such as potassium chloride (KCl), potassium iodide (KI), and potassium bromide (KBr), ceric oxide (CeO_2), gypsum, elemental sulfur (S), charcoal (C), and possible combinations

TOP SECRET

thereof.

At least some of such compounds may be found in HAWLEY'S CONDENSED CHEMICAL DICTIONARY, THIRTEENTH EDITION, revised by Richard J. Lewis, Sr., John Wiley & Sons, Inc., New York, ISBN #0-471-29205-2 (hardcover). They may possibly also be found in THE MERCK INDEX, An Encyclopedia of Chemicals, Drugs, and Biologicals, ELEVENTH EDITION, Susan Budavari, Editor, published by MERCK & CO., INC., Rahway, N.J., 1989, ISBN #911910-28-X.

Features relating to fining agents, which features may possibly be used in an embodiment of the present invention may be found in U.S. Pat. No. 3,954,656 issued to Deeg et al. on May 4, 1976 and entitled "Laser glasses with high damage threshold and method of making such glasses"; U. S. Pat. No. 4,038,090 issued to Gliemroth on July 26, 1977 and entitled "Ion exchangeable glass having low thermal expansion"; U.S. Pat. No. 4,119,760 issued to Rinehart on October 10, 1978 and entitled "Chemical strengthening of glass"; U.S. Pat. No. 4,138,235 issued to Turner on February 6, 1979 and entitled "Method of making flat glass with lower sulfur-containing emissions"; U.S. Pat. No. 4,313,747 issued to Barton on February 2, 1982 and entitled "Process for making glass with agglomerated refining agents"; U.S. Pat. No. 4,360,567 issued to Guillevic on November 23, 1982 and entitled "Easy-to-clean glass or glass-ceramic cookware in the alkaline earth metal oxide-Al₂O₃-SiO field"; U.S. Pat. No. 4,607,016 issued to Danielson et al. on August 19, 1986 and entitled "Glass for use as tungsten-halogen lamp envelopes"; U.S. Pat. No. 5,006,144 issued to Knavish et al. on April 9, 1991 and entitled "Melting glass with oxidation control and lowered emission"; U.S. Pat. No. 5,547,904 issued to Watzke et al. on August 20, 1996 and entitled "Borosilicate glass having improved UV transmission, thermal and chemical properties and methods of making and using same; U.S. Pat. No. 5,922,097 issued to Kobayashi et al. on July 13, 1999 and entitled "Water enhanced fining process a method to

2025-04-06 16:28:50

reduce toxic emissions from glass melting furnaces; and U.S. Pat. No. 6,128,430 issued to Chu et al. on October 3, 2000 and entitled "Composition for optical waveguide article and method for making continuous clad filament", all of these U.S. patents being hereby expressly incorporated by reference as if set forth in their entirety herein.

Coloring agents that may possibly be used with the glass of the present invention comprise, for example, compounds of vanadium (V), such as vanadium pentoxide (V_2O_5), chromium (Cr), such as chromic oxide (Cr_2O_3), manganese (Mn), such as manganese dioxide (MnO_2), iron (Fe), such as iron oxide (Fe_2O_3), cobalt (Co), such as cobalt oxide (CoO), copper (Cu), such as copper monoxide (CuO), nickel (Ni), such as nickel oxide (NiO), and selenium (Se), and/or chlorine (Cl) compounds, and possible combinations thereof.

At least some of such compounds may be found in HAWLEY'S CONDENSED CHEMICAL DICTIONARY, THIRTEENTH EDITION, revised by Richard J. Lewis, Sr., John Wiley & Sons, Inc., New York, ISBN #0-471-29205-2 (hardcover). They may possibly also be found in THE MERCK INDEX, An Encyclopedia of Chemicals, Drugs, and Biologicals, ELEVENTH EDITION, Susan Budavari, Editor, published by MERCK & CO., INC., Rahway, N.J., 1989, ISBN #911910-28-X.

Features relating to coloring agents, which features may possibly be incorporated in an embodiment of the present invention, may be found in U.S. Pat. No. 4,397,667 issued to Morimoto et al. on August 9, 1983 and entitled "Method of coloring glass sheet by diffusion and reduction of silver ions"; and U.S. Pat. No. 5,089,444 issued to Hattori et al. on February 18, 1992 and entitled "Method of producing colored crystallized glass", all of these U.S. patents being hereby expressly incorporated by reference as if set forth in their entirety herein.

Some examples of features relating to prestressing of glass

050229409-040501

or prestressable glass, including the use of potassium and the like chemical prestressing, which features may possibly be incorporated in an embodiment of the present invention may be found in U.S. Pat. No. 3,984,252 issued to Kiefer on October 5, 1976 and entitled "Fireproof glass windowpanes"; U.S. Pat. No. 4,259,118 issued to Sack on March 31, 1981 and entitled "Thermally high pre-stressable glass with high hot stressing factors"; U.S. Pat. No. 4,671,814 issued to Aratani et al. on June 9, 1987 and entitled "Method of strengthening glass article formed of float glass by ion exchange"; U.S. Pat. No. 4,715,879 issued to Schmitte et al. on December 29, 1987 and entitled "Method for the manufacture of a tempered an/or curved glass pane with reduced transmission"; U.S. Pat. No. 5,846,280 issued to Speit on December 8, 1998 and entitled "Process for production of chemically prestressed glass"; and U.S. Pat. No. 5,895,768 issued to Speit on April 20, 1999 and entitled "Chemically prestressable aluminosilicate glass and products made therefrom", all of these U.S. patents being hereby expressly incorporated by reference as if set forth in their entirety herein.

Although only a few exemplary embodiments of this invention have been described in detail above, those skilled in the art will readily appreciate that many modifications are possible in the exemplary embodiments without materially departing from the novel teachings and advantages of this invention. Accordingly, all such modifications are intended to be included within the scope of this invention as defined in the following claims. In the claims, means-plus-function clauses are intended to cover the structures described herein as performing the recited function and not only structural equivalents but also equivalent structures.

The invention as described herein above in the context of the preferred embodiments is not to be taken as limited to all of the provided details thereof, since modifications and variations

09329409-040504

NHL-FMW-02A US(SCT)

thereof may be made without departing from the spirit and scope
of the invention.

09829409 0403001

NHL:ktp/smj

T05040" 60462350

Table 1: Compositions and characteristics of float glasses

Example No.	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17
Composition (wt.%) on oxide basis:																	
Li ₂ O	4.1	4.17	3.85	3.8	3.8	4.3	3.65	4.2	4.2	4.0	4.25	4.15	3.8	4.4	3.8	3.8	3.8
Na ₂ O	0.4	0.37	0.56	0.7	0.2	0.6	0.2	0.3	0.5	0.45	0.4	0.48	0.8	0.4	0.6	0.6	0.6
K ₂ O	0.3	0.35	-	-	0.5	0.3	0.5	0.3	0.2	0.20	0.21	0.1	-	0.2	-	-	-
MgO	0.55	1.10	0.46	0.9	1.3	1.2	1.5	1.1	1.05	1.0	1.2	1.0	1.4	0.5	0.5	0.5	0.5
CaO	-	-	-	0.5	1.0	-	0.5	-	0.5	-	-	1.3	-	0.5	-	-	-
BaO	-	-	2.03	1.0	-	2.2	-	-	-	-	-	-	-	1.2	2.0	2.0	2.0
ZnO	-	-	1.40	-	-	-	0.4	-	-	-	-	-	-	-	1.7	1.7	1.7
Al ₂ O ₃	22.9	22.5	22.34	22.2	21.8	21.2	23.4	23.2	22.2	21.8	22.7	22.0	21.0	21.8	22.3	22.3	22.3
SiO ₂	66.1	65.62	65.1	65.5	66.3	65.2	64.1	64.4	65.75	67.4	65.54	65.55	66.5	64.9	65.0	65.0	65.0
TiO ₂	2.1	2.15	1.9	2.3	1.9	2.0	1.95	2.05	2.05	2.45	2.18	2.05	1.9	2.1	2.4	2.4	2.4
ZrO ₂	2.05	2.0	1.96	1.9	2.05	2.1	2.00	2.20	2.05	1.75	1.95	2.0	2.0	1.8	1.7	1.7	1.7
SnO ₂	0.15	0.24	0.4	0.2	0.15	0.3	0.10	0.25	0.20	0.25	0.24	0.27	0.4	0.3	-	-	-
P ₂ O ₅	1.35	1.3	-	1.0	1.2	0.6	1.7	2.0	1.3	0.7	1.33	1.1	2.2	2.0	-	-	-
Misc.															0.3 As ₂ O ₃	900 ppb Pt	
Σ	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0
Tg (°C)	703	694	682	704	698	671	688	695	697	702	684	683	698	686	n.d.	679	n.d.
VA (°C)	1342	1334	1331	1331	1337	1317	1312	1310	1317	1337	1320	1310	1342	1329	n.d.	1295	n.d.
α _{10/300} (10 ⁻⁶ /K)	4.0	4.1	4.1	4.2	4.0	4.6	4.0	4.2	4.3	4.0	4.2	4.4	4.0	4.4	n.d.	4.1	n.d.
Light transmittance (t), 4 mm thickness	90.5	91.4	89.9	87.9	90.1	89.7	90.5	90.0	90.1	90.3	90.7	90.2	89.5	90.5	n.d.	n.d.	n.d.

n.d. = not measured

Table 2: Transformation conditions and characteristics of the glass ceramics claimed by the invention

Example No.	1	2	3	4	5	6	7	8	9	10	11	12	13	14
Transformation conditions														
Nucleation (°C), (min)	755 60	755 60	760 60	750 60	750 60	740 60	745 60	755 60	750 60	755 60	740 60	735 60	730 60	730 60
Crystallization (°C) (min)	918 15	903 15	896 15	909 15	910 15	889 15	904 15	899 15	898 15	910 15	898 15	892 15	908 15	910 15
Keatite transformation (°C) (min)											1020 60			
Ceramicized characteristic s: Crystal phases	hQMK	hQMK	hQMK	hQMK	hQMK	hQMK	hQMK	hQMK	hQMK	hQMK	Keatite MK	hQMK	hQMK	hQMK
Crystallite Size (nm)	42	40	42	48	55	56	61	50	47	50	n.d.	51	43	44
Appearance	trans- parent	trans- parent	trans- parent	trans- parent	trans- parent	trans- parent	trans- parent	trans- parent	trans- parent	trans- parent	white trans- parent	trans- parent	trans- parent	trans- parent
$\alpha_{20/100}$ (10 ⁻⁴ /K)	-0.34	0.03	-0.20	0.31	0.47	0.53	0.57	0.04	0.15	0.02	1.17	0.26	0.24	-0.29
Light transmittance (%), 4 mm thickness	84.7	84.8	80.8	83.0	83.9	73.4	83.5	84.9	84.3	79.1	18.8	83.5	83.3	82.3

n.d. = not determined

hQMK = High quartz mixed crystals